

BS ISO 16560:2015



BSI Standards Publication

**Surface active agents —
Determination of polyethylene
glycol content in nonionic
ethoxylated surfactants —
HPLC method**

National foreword

This British Standard is the UK implementation of ISO 16560:2015.

The UK participation in its preparation was entrusted to Technical Committee CII/34, Methods of test for surface active agents.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 77090 6

ICS 71.100.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2015.

Amendments issued since publication

Date	Text affected
------	---------------

**Surface active agents —
Determination of polyethylene glycol
content in nonionic ethoxylated
surfactants — HPLC method**

Agents de surface tensioactifs — Dosage de la teneur en polyéthylène glycol dans les surfactants éthoxylés non ioniques — Méthode par CLHP



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Sampling	2
7.1 Preparation of the test sample	2
7.2 Preparation of test solutions.....	2
8 Procedure	3
8.1 Apparatus settings.....	3
8.2 Calibration	3
8.2.1 Preparation of calibration solutions	3
8.2.2 Calibration curve	4
8.3 Determination	4
9 Expression of results	5
10 Precision	5
10.1 Repeatability.....	5
10.2 Reproducibility.....	5
11 Test report	5
Annex A (informative) Results of interlaboratory tests for fatty alcohol ethoxylate	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 91, *Surface active agents*.

Introduction

This International Standard was developed based on EN 12582.

Surface active agents — Determination of polyethylene glycol content in nonionic ethoxylated surfactants — HPLC method

1 Scope

This International Standard specifies a method for the determination of the polyethylene glycol (PEG) content in aromatic and aliphatic non-ionic surface active agents of the type $R-(O-C_2H_4)_n OH$; where n is the mean ethylene oxide (EO) value. It is applicable to all ethoxylated products soluble in methanol or methanol/water mixture. This method applies to PEG concentrations as mass fraction greater than or equal to 0,1 %. This International Standard is not applicable to PEG whose molar mass is lower than 400 g/mol. Monomeric ethylene glycol, diethylene glycol, triethylene glycol, and glycerol are not detected.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 607, *Surface active agents and detergents — Methods of sample division*

ISO 5725-2, *Accuracy (trueness and precision) measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

polyethylene glycol content

amount of polyethylene glycol, expressed as a percentage by mass, calculated from the calibration curve in accordance with this International Standard

4 Principle

Polyethylene glycol is separated from the polyethoxylated surface active agents by means of reversed phase liquid chromatography. In this process PEG is eluted in the first minutes while the non-ionic surface active agents are retarded. Evaporative light scattering detector (ELSD) or charged aerosol detector (CAD) does not detect volatile materials such as the sample solvent; interferences with the PEG peak are limited. The sample is dissolved in an 80/20 (V/V) mixture of methanol/water or in another methanol/water mixture to obtain a clear solution. A portion of the sample solution is then analysed by high performance liquid chromatography (HPLC). Quantification of PEG content is achieved by external calibration with PEG molar mass equal to 1 000 g/mol.

5 Reagents

During the analysis, use only reagents of recognized analytical grade and the water used shall conform to grade 3 in accordance with ISO 3696.

5.1 Polyethylene glycol, with molar mass of 1 000 g/mol, gel permeation chromatography (GPC) grade.