

INTERNATIONAL STANDARD

ISO
16893

First edition
2016-01-15

Corrected version
2016-03-15

Wood-based panels — Particleboard

Panneaux à base de bois — Panneaux de particules



Reference number
ISO 16893:2016(E)

© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	2
3.1 Terms and definitions.....	2
3.2 Abbreviated terms.....	2
4 Classifications	2
4.1 Classification matrices.....	2
4.2 Uses.....	3
4.3 Additional classifications.....	3
4.4 Structural grades.....	4
5 Tests related to each class of particleboard	4
5.1 Mandatory tests.....	4
5.2 Optional tests.....	4
6 Thickness ranges	5
7 Expression of specification limits and general requirements	5
7.1 Expression of specification limits.....	5
7.2 Lower specification limits.....	5
7.3 Upper specification limits.....	6
7.4 Moisture resistance requirement options.....	6
7.5 Density variation, dimension and moisture content requirements.....	6
7.6 Formaldehyde requirements.....	6
7.7 Load bearing particleboard.....	7
8 Specific property requirements	7
8.1 Requirements for general purpose particleboard for use in dry conditions (P-GP REG).....	7
8.2 Requirements for furniture grade particleboard for use in dry conditions (P-FN REG).....	8
8.3 Requirements for load bearing particleboard for use in dry conditions (P-LB REG).....	8
8.4 Requirements for heavy-duty load bearing particleboard for use in dry conditions (P-HLB REG).....	9
8.5 Requirements for general purpose particleboard for use in temperate humid conditions (P-GP MR1).....	9
8.6 Requirements for furniture grade particleboard for use in temperate humid conditions (P-FN MR1).....	10
8.7 Requirements for load bearing particleboard for use in temperate humid conditions (P-LB MR1).....	11
8.8 Requirements for heavy-duty load bearing particleboard for use in temperate humid conditions (P-HLB MR1).....	12
8.9 Requirements for general purpose particleboard for use in high tropical humid conditions (P-GP MR2).....	13
8.10 Requirements for furniture grade particleboard for use in high tropical humid conditions (P-FN MR2).....	14
8.11 Requirements for load bearing particleboard for use in tropical humid conditions (P-LB MR2).....	15
8.12 Requirements for heavy-duty load bearing particleboard for use in high tropical humid conditions (P-HLB MR2).....	16
9 Marking	16
Annex A (normative) Calculation of 5-percentile and 95-percentile values	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 89, *Wood-based panels*, Subcommittee SC 2, *Particle boards*.

This first edition cancels and replaces ISO 16893-1:2008 and ISO 16893-2:2010, which have been technically revised.

This corrected version of ISO 16893:2016 incorporates the following corrections.

The revision statement has been corrected in the Foreword, correctly identifying the documents which this International Standard cancels and replaces.

The footer ^a in Table 4 has been amended and changed to NOTE 2.

The expression of thickness ranges have been corrected in the headers in Tables 5 to 16.

Wood-based panels — Particleboard

1 Scope

This International Standard specifies a classification matrix and the related mandatory tests and thickness ranges to be applied to wood-based particleboard for general purposes, furniture, load-bearing applications and heavy-duty load-bearing applications. It then provides the manufacturing property requirements for these types of uncoated particleboard.

The values listed in this International Standard relate to product properties used to classify particleboards into one of four grades (P-GP, P-FN, P-LB or P-HLB, see [Clause 3](#)), for use in three service conditions (REG, MR1 and MR2). The values are not characteristic values to be used for design purposes.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3340, *Fibre building boards — Determination of sand content*

ISO 9426, *Wood-based panels — Determination of dimensions of panels*

ISO 9427, *Wood-based panels — Determination of density*

ISO 12460-1, *Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the 1-cubic-metre chamber method*

ISO 12460-3, *Wood-based panels — Determination of formaldehyde release — Part 3: Gas analysis method*

ISO 12460-4, *Wood-based panels — Determination of formaldehyde release — Part 4: Desiccator method*

ISO 12460-5, *Wood-based panels — Determination of formaldehyde release — Part 5: Extraction method (called the perforator method)*

ISO 16572, *Timber structures — Wood-based panels — Test methods for structural properties*

ISO 16978, *Wood-based panels — Determination of modulus of elasticity in bending and of bending strength*

ISO 16979, *Wood-based panels — Determination of moisture content*

ISO 16981, *Wood-based panels — Determination of surface soundness*

ISO 16983, *Wood-based panels — Determination of swelling in thickness after immersion in water*

ISO 16984, *Wood-based panels — Determination of tensile strength perpendicular to the plane of the panel*

ISO 16985, *Wood-based panels — Determination of dimensional changes associated with changes in relative humidity*

ISO 16987, *Wood-based panels — Determination of moisture resistance under cyclic test conditions*

ISO 16998, *Wood-based panels — Determination of moisture resistance — Boil test*

ISO 17064, *Wood-based panels — Fibreboard, particleboard and oriented strand board (OSB) — Vocabulary*

ISO 20585:2005, *Wood-based panels — Determination of wet bending strength after immersion in water at 70 degrees C or 100 degrees C (boiling temperature)*